

CHEMICAL PROPERTIES OF VULKOLLAN®

	Swelling in % by weight	Evaluation of stability
Water	< 2	+
ASTM oil I	< 2	++
ASTM oil II	< 2	++
ASTM oil II	< 10	0
Light fuel oil	< 5	+
Transformer oil	< 2	++
Dry cleaning fluid	< 10	0
Benzene	< 100	--
Toluene	< 100	--
Methylene Chloride	< 300	--
Carbon tetrachloride	< 100	--
Trichloroethane	< 200	--
Methanol	< 10	0
Ethanol	< 10	0
Ethyl acetate	< 50	-
Acetone	< 50	-

++ very good, + good, 0 satisfactory, - moderate, -- not suitable